

PRODUCT DATA

COATING PRT

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Solvent based acrylic paint.

MAIN PROPERTIES

Unsanonifiable - flexible.

RECOMMENDED USES

- Coating of inner and outer walls that can be exposed to high humidity, f.i. bathrooms, kitchens, etc.
- Topcoat on Dacfill (improved resistance against stagnating water and less dirt retention) or on Noxyde (less dirt retention).

TECHNICAL DATA

Appearance:	Satin gloss (gloss 60°: ± 48%)
Colour:	White, grey, Dacfill grey
Density:	1.10 - 1.14 g/cm ³
Solids Content:	In volume: 41 - 43% In weight: 46 - 49%
Recommended film thickness:	Wet film: 140 micron (cons.: 7 m ² /l) Dry film: 60 micron (cons.: 7 m ² /l)
VOC-content:	Max. 600 g/l
VOC-content:	481 g/l max.
Ready-for-use mixture:	499 g/l max.
Category:	A/i
EU Limit values:	600 g/l (2007) / 500 g/l (2010)

Drying times 20°C/50% r.h.

To touch:	3 hours
To handle:	4 hours
To recoat:	24 hours
Full hardness:	24 hours

Coverage

Theoretical:	6 - 8 m ² /l
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Clean the substrate. Allow to dry, any previous coatings must be completely dry.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush:	All types.
Roller:	Short nap-mohair roller
Air-atomised spray:	Do not dilute

PRODUCT DATA

COATING PRT

Airless spray: Nozzle: 4/15 - Pressure: 100 bars

Cleanup: Thinner 22 or white spirit

APPLICATION CONDITIONS

Work in a dry and well-ventilated area.

REMARKS

- a) Reversible paint system, this means that the product dissolves in its own solvent.
- b) Can be applied on new concrete.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk