

## PRODUCT DATA

## Dacfill SB Top Coat

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk

### DESCRIPTION

Liquid applied 1 component ultra high solids moisture activated elastomeric urethane coating. Topcoat for the Dacfill SB waterproofing system.

### MAIN PROPERTIES

High build coating that provides a durable, long term waterproofing system. Dacfill SB is to be used as topcoat on Dacfill SB Embedment Coat.

### RECOMMENDED USES

For all types of pitched and flat roofs. Used as waterproofing topcoat in reinforced and unreinforced Dacfill SB waterproofing membrane systems.

### TECHNICAL DATA

Appearance:	Semi Gloss
Colour:	Dove Grey
Density:	1.28 kg/litre
Solids Content:	In volume: 80%
	In weight: Approx 85%
Recommended film thickness:	Wet film: 0.5 - 1.0 mm per coat (depending on system)
	Dry film: 0.4 - 0.8 mm per coat (depending on system)
VOC-content:	262 g/l max.
Ready-for-use mixture:	262g/l max.
Category:	A/i
EU Limit values:	600 g/l (2007) / 500 g/l (2010)

**Drying times** 20°C/50% r.h.

To touch: 4 hours

To recoat: 12 hours and within 7 days

Full hardness 16 hours

Note: Drying/curing times will be shortened by higher temperatures and lengthened by lower temperatures

### Coverage

Theoretical: 1 - 2m<sup>2</sup> per litre per coat

Practical: Dependant on surface profile, reinforcement where applicable etc.

### SURFACE PREPARATION

Dacfill SB Topcoat is to be used as a topcoat on Dacfill SB Embedment Coat.

Contact Technical Service department for further advice.

### DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

### APPLICATION & THINNING

Brush: Possible, do not dilute.

Roller: Possible, do not dilute.

Air-atomised spray: Possible, do not dilute.

Airless spray: Possible, do not dilute.

Cleanup: Thinner 160.

**PRODUCT DATA**

**Dacfill SB Top Coat**

**APPLICATION CONDITIONS**

Minimum 5°C in well ventilated areas and fair conditions.

**SAFETY**

Consult Safety Data Sheet and Safety Information printed on the can.

**SHELLIFE / STORAGE CONDITIONS**

12 months from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at maximum 25°C.

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

[info@mathysdirect.co.uk](mailto:info@mathysdirect.co.uk)  
[www.mathysdirect.co.uk](http://www.mathysdirect.co.uk)