

PRODUCT DATA

Dacfill SB Top Coat

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Liquid applied 1 component ultra high solids moisture activated elastomeric urethane coating. Topcoat for the Dacfill SB waterproofing system.

MAIN PROPERTIES

High build coating that provides a durable, long term waterproofing system. Dacfill SB is to be used as topcoat on Dacfill SB Embedment Coat.

RECOMMENDED USES

For all types of pitched and flat roofs. Used as waterproofing topcoat in reinforced and unreinforced Dacfill SB waterproofing membrane systems.

TECHNICAL DATA

Appearance:	Semi Gloss
Colour:	Dove Grey
Density:	1.28 kg/litre
Solids Content:	In volume: 80%
	In weight: Approx 85%
Recommended film thickness:	Wet film: 0.5 - 1.0 mm per coat (depending on system)
	Dry film: 0.4 - 0.8 mm per coat (depending on system)
VOC-content:	262 g/l max.
Ready-for-use mixture:	262g/l max.
Category:	A/i
EU Limit values:	600 g/l (2007) / 500 g/l (2010)

Drying times 20°C/50% r.h.

To touch: 4 hours

To recoat: 12 hours and within 7 days

Full hardness 16 hours

Note: Drying/curing times will be shortened by higher temperatures and lengthened by lower temperatures

Coverage

Theoretical: 1 - 2m² per litre per coat

Practical: Dependant on surface profile, reinforcement where applicable etc.

SURFACE PREPARATION

Dacfill SB Topcoat is to be used as a topcoat on Dacfill SB Embedment Coat.

Contact Technical Service department for further advice.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush: Possible, do not dilute.

Roller: Possible, do not dilute.

Air-atomised spray: Possible, do not dilute.

Airless spray: Possible, do not dilute.

Cleanup: Thinner 160.

PRODUCT DATA

Dacfill SB Top Coat

APPLICATION CONDITIONS

Minimum 5°C in well ventilated areas and fair conditions.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

12 months from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at maximum 25°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk