

PRODUCT DATA

DIVALO

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Waterborne varnish based on pure acrylic resins.

MAIN PROPERTIES

Does not yellow - easy application with roller or brush - uniform finish - washable.

RECOMMENDED USES

Finish on indoor paints and decorative paint systems when a high mechanical resistance is required. Recommended as a topcoat on decorative paint systems (Fair-Decor).

TECHNICAL DATA

Appearance:	Satin gloss (gloss 60°): ± 20%
Colour:	Colourless
Density:	1,02 - 1,06 g/cm ³
Solids Content:	In volume: 27.5 - 30.5% In weight: 30 - 33%
Recommended film thickness:	Wet film: ± 70 micron (cons.: 14 m ² /l) Dry film: ± 20 micron (cons.: 14 m ² /l)
Flashpoint:	Not flammable
VOC-gehalte:	90 g/l max.
Gebbruiksklaar mengsel:	90 g/l max.
Categorie:	A/e
EU grenswaarde:	150 g/l (2007) / 130 g/l (2010)

Drying times	20°C/50% r.h.
To touch:	30 minutes
To recoat:	4 hours
Full hardness	± 1 week

Coverage

Theoretical: 12 - 14 m²/l

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Clean and degrease substrate. The paint coats or systems that have to be protected have to be dry and/or fully cured.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush: Apply in 1 or 2 coats with flat brush. If necessary dilute with water.

Roller: Apply in 1 or 2 coats with lacquer. If necessary dilute with water.

Air-atomised spray: If necessary dilute with water.

Airless spray: Nozzle: 09 - 013 / Pressure: 180 bars

Cleanup: Water

PRODUCT DATA

DIVALO

APPLICATION CONDITIONS

Min. temperature 5°C and max. 80% R.H.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk