

PRODUCT DATA

FAIRCLEAN

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Waterborne washable mat paint for interior walls with acrylic resins

MAIN PROPERTIES

Combines a mat appearance with a not porous washable surface (coffee spots, wine, waterborne etc. can be easily removed without changing the aspect of the paint) - strong mechanical resistance - easy to apply and fast dry - very good hiding.

RECOMMENDED USES

Finish for walls which will be often washed (children rooms, kitchens, bathrooms, stairways, etc.)

TECHNICAL DATA

Appearance:	Mat ($^{\circ}60: \pm 3 \%$)
Colour:	White
Density:	+/- 1.42-1.5 g/cm ³
Solids Content:	In volume: 40 - 43 % In weight: 59 – 62 %
Recommended film thickness:	Wet film: 125 μm (cons.: 8 m ² /l) Dry film: 50 μm (cons.: 8 m ² /l)
Flashpoint:	Not flammable
VOC-content:	70 g/l max.
Ready to use mixture:	70 g/l max.
Category:	A/i
EU Limit values:	140 g/l (2007) / 140 g/l (2010)

Drying times 20°C/60% r.h.

To touch: 15 minutes

To recoat: 1 hour

Full hardness: 1 day

Coverage

Theoretical: 7 - 9 m²/l

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Apply direct on non porous, clean, dry and stable substrates.

Porous substrates, or painted substrates, first prime with Pegafix or with a diluted layer (4 parts Fairclean + 1 part Pegafix). Humid stains or nicotine stains, to isolate with a layer Pegamat RL.

DIRECTION FOR USE

Before application stir the product till complete homogenous.

PRODUCT DATA

FAIRCLEAN

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

APPLICATION & THINNING

Brush: Do not dilute.
Roller: Do not dilute.
Air-atomised spray: Do not dilute.
Airless spray: Nozzle: 013 - 015/ pressure: 180 bar. Do not dilute.
Cleanup: Water

APPLICATION CONDITIONS

Apply by a min. temperature of 5°C, and RH of max. 80 %

REMARKS

In order to avoid overlaps work wet in wet in case of roller application.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.