

PRODUCT DATA

FAIRTEX

DESCRIPTION

Waterbased matt acrylic dispersed paint for indoor walls and ceilings.

MAIN PROPERTIES

Easy and completely spatter-free roller application - even flat finish without overlaps - covers perfectly in 2 coats on most kinds of porous and not porous substrates without gloss differences - nearly odourless - high whiteness degree.

RECOMMENDED USES

Inner decoration on most common substrates such as plaster, bricks and concrete. Also old paint coats in good condition and most wallpaper can be recoated with Fairtex.

TECHNICAL DATA

Appearance:	Matt (gloss 60°: 2%)
Colour:	White
Density:	1,38 - 1,41 g/cm ³
Solids Content:	In volume: 28 - 32% In weight: 48 - 51%
Recommended film thickness:	Wet film: ± 140 micron (cons.: 7 m ² /l) Dry film: ± 45 micron (cons.: 7 m ² /l)
Flashpoint:	Not flammable
Sanding resistance:	> 5.000 cycles (DIN 53778)
VOC-content:	30 g/l max.
Ready-for-use mixture:	30 g/l max.
Category:	A/a
EU Limit values:	75 g/l (2007) / 30 g/l (2010)

Drying times 20°C/50% r.h.

To touch:	30 minutes
To handle:	Not applicable
To recoat:	3 hours
Full hardness:	± 1 week

Coverage

Theoretical:	6 - 8 m ² /l
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Always work on a dry and stable substrate. On porous substrates, no specific pre-treatment is required in most cases. Slightly chalking substrates or new plaster should first be impregnated with Pegafix. Damp substrates or nicotine stains should be isolated with Pegamat.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush:	Apply undiluted.
Roller:	Apply undiluted.
Air-atomised spray:	Not recommended.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

PRODUCT DATA

FAIRTEX

Airless spray: If necessary, dilute with 2 - 5% of water.
Nozzle: 016 - 018 / Pressure: 200 bars.

Cleanup: Water.

APPLICATION CONDITIONS

Apply at a temperature of min. 5°C and a R.H. of max. 80%.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk