

## PRODUCT DATA

## FASSICLOR

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk

### DESCRIPTION

Solvent borne chlorinated rubber paint.

### MAIN PROPERTIES

Alkali and acid resistant - excellent water resistance - U.V. stable.

### RECOMMENDED USES

Decorative painting of swimming pools or ponds in concrete.

### TECHNICAL DATA

Appearance:	Satin gloss (gloss 60°): ± 47%
Colour:	White, azure blue, water green, pearl grey
Density:	1.2 - 1.3 g/cm <sup>3</sup>
Solids Content:	In volume: 28 - 33% In weight: 49 - 56%
Recommended film thickness:	Wet film: ± 165 micron (cons.: 6 m <sup>2</sup> /l) Dry film: ± 50 micron (cons.: 6 m <sup>2</sup> /l)
VOC-content:	Max. 640 g/l
Flashpoint:	> 39°C

### Drying times 20°C/50% r.h.

To touch:	1½ hours
To handle:	3 hours
To recoat:	24 hours
Full hardness	12 days

### Coverage

Theoretical:	2 coats of ± 6 m <sup>2</sup> /l per coat
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

### SURFACE PREPARATION

Apply without priming coat on an old chlorinated rubber paint (after cleaning) or on a hardened and dry concrete substrate (maximum humidity degree 5%). Attention: since Fassiclor is no waterproofing product, the concrete substrate must be waterproof!

### DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

### APPLICATION & THINNING

Brush:	If necessary, dilute slightly with Thinner 22.
Roller:	Apply the first coat with brush by preference, if necessary dilute slightly with Thinner 22.
Air-atomised spray:	If necessary, dilute slightly with Thinner 22.
Airless spray:	Dilute with ± 10 – 20% Thinner 22. Nozzle: 018 / Pressure: 200 bars.
Cleanup:	Thinner 22

## PRODUCT DATA

## FASSICLOR

### APPLICATION CONDITIONS

Apply in a dry and well-ventilated area.

### REMARKS

When using in indoor swimming pools, especially during airless spraying, it is advisable to wear a mask due to limited ventilation.

### SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

### SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

[info@mathysdirect.co.uk](mailto:info@mathysdirect.co.uk)  
[www.mathysdirect.co.uk](http://www.mathysdirect.co.uk)