

PRODUCT DATA

FASSILUX SATIN

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Solvent based satin gloss enamel based on soya-alkyd resins.

MAIN PROPERTIES

Easy to apply - quick drying - extremely durable - high solids content - hard but flexible film.

RECOMMENDED USES

Topcoat for interior and exterior woodwork.

TECHNICAL DATA

Appearance:	Satin gloss
Colour:	White + colour chart + Mathymix colours
Density:	1,34 - 1,37 g/cm ³
Solids Content:	In volume: 53 - 56% (white) In weight: 70 - 73% (white)
Recommended film thickness:	Wet film: ± 55 micron (cons.: 18 m ² /l) Dry film: ± 30 micron (cons.: 18 m ² /l)
Flashpoint:	> 39°C
VOC ready-for-use mixture:	300 g/l max.
Category:	A/d
EU Limit values:	400 g/l (2007) / 300 g/l (2010)

Drying times 20°C/50% r.h.

To touch:	4 - 5 hours
To handle:	5 - 6 hours
To recoat:	24 hours
Full hardness:	± 1 week

Coverage

Theoretical:	± 18 m ² /l
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Priming coat: Fassiprim. For top quality painting work, apply two coats of Fassiprim, sanding between each coat carefully. For exterior works, it is advisable to apply an impregnating coat of Adex on bare or stripped wood.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush:	Do not dilute.
Roller:	Do not dilute.
Air-atomised spray:	Do not dilute.

PRODUCT DATA

FASSILUX SATIN

Airless spray: Nozzle: 013 - 015 / Pressure: 180 bars.
Do not dilute.

Cleanup: White spirit or Thinner 22

APPLICATION CONDITIONS

Apply in a dry and well-ventilated area.
Minimum temperature: 10°C. Maximum relative humidity: 80%.

REMARKS

Do not use Fassilux Satin on Noxyde for outside works. In these cases, use either Fassilux or Pegacryl Satin.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk