

## PRODUCT DATA

## FASSILUX

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk

### DESCRIPTION

Solvent based high gloss enamel based on alkyd resins.

### MAIN PROPERTIES

Easy to apply - quick drying - extremely durable - high solids content - hard but flexible film.

### RECOMMENDED USES

Topcoat for interior and exterior woodwork.

### TECHNICAL DATA

Appearance:	Gloss (gloss 60°: > 90%
Colour:	White + colour chart + Mathymix colours
Density:	1,21 - 1,24 g/cm <sup>3</sup> (white)
Solids Content:	In volume: 61 - 64% (white) In weight: 74 - 78% (white)
Recommended film thickness:	Wet film: ± 50 micron (cons.: 20 m <sup>2</sup> /l) Dry film: ± 30 micron (cons.: 20 m <sup>2</sup> /l)
Flashpoint:	> 39°C
VOC Ready-for-use mixture:	300 g/l max.
Category:	A/d
EU Limit values:	400 g/l (2007) / 300 g/l (2010)

### Drying times 20°C/50% r.h.

To touch:	± 3 hours
To handle:	± 4 hours
To recoat:	24 hours
Full hardness	± 1 week

### Coverage

Theoretical:	± 20 m <sup>2</sup> /l per coat
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

### SURFACE PREPARATION

For top quality work, apply two coats of Fassiprim, sanding between each coat carefully. In some cases, the 2 coats of Fassiprim can be replaced by 1 thick coat of Fassicoat. For exterior works, it is advisable to apply an impregnating coat of Adex on bare or stripped wood.

### DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

### APPLICATION & THINNING

Brush:	Do not dilute.
Roller:	Do not dilute.
Air-atomised spray:	Do not dilute.

**PRODUCT DATA**

**FASSILUX**

Airless spray:            Nozzle: 09 - 013 / Pressure: 180 bars.  
Do not dilute.

Cleanup:                White spirit or Thinner 22.

**APPLICATION CONDITIONS**

Apply in a dry and well-ventilated area.  
Temperature minimal 10°C. Relative humidity max. 80%.

**REMARKS**

Apply Fassilux in thin layers.

**SAFETY**

Consult Safety Data Sheet and Safety Information printed on the can.

**SHELLIFE / STORAGE CONDITIONS**

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

[info@mathysdirect.co.uk](mailto:info@mathysdirect.co.uk)  
[www.mathysdirect.co.uk](http://www.mathysdirect.co.uk)