

PRODUCT DATA

FASSITEK

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Solvent based wood preservative based on special linseed oil alkyd resins.

MAIN PROPERTIES

Protective and decorative impregnation of interior and exterior woodwork.
Remark: colourless Fassitek is only suitable for internal use.

RECOMMENDED USES

Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance - microporous, so no risk of blisters or peeling off - easier maintenance - not a film former.

TECHNICAL DATA

Appearance:	Satin gloss
Colour:	10 wood tints + colourless (see colour chart)
Density:	0,87 - 0,90 g/cm ³
Solids Content:	In volume: ± 30% In weight: ± 38%
Recommended film thickness:	Wet film: ± 100 micron (cons.: 10 m ² /l) Dry film: ± 30 micron (cons.: 10 m ² /l)
Flashpoint:	>39°C
VOC-content:	565 g/l max.
Ready-for-use mixture:	565 g/l max.
Category:	A/f
EU Limit values:	700 g/l (2007) / 700 g/l (2010)

Drying times 20°C/50% r.h.

To touch:	± 3 hours (15 m ² /l)
To handle:	± 3 hours (15 m ² /l)
To recoat:	24 hours

Coverage

Theoretical:	± 10 - 15 m ² /l
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit, Afzelia with ammonia water.
Old stripped paint: rub down up to the bare not impregnated wood fibre and make dust free.
Maintenance on Fassitek: clean substrate with white spirit and apply 2 or 3 thin coats.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush:	By preference, apply undiluted.
Roller:	By preference, apply undiluted.
Air-atomised spray:	By preference, apply undiluted.

PRODUCT DATA

FASSITEK

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

Airless spray: By preference, apply undiluted.
Nozzle: 09 - 013 / Pressure: 150 bars.

Cleanup: White spirit or Thinner 22

APPLICATION CONDITIONS

Apply in a dry and well-ventilated area.

REMARKS

Incorrect use of Fassitek means that it can still be fully or partly removed with Thinner 22 within the first few days after application.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.