

PRODUCT DATA

FASSITOP

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Solvent based wood finisher based on soya-/linseed oil alkyd resins.

MAIN PROPERTIES

Transparent and colour fast - excellent UV-rays and weather resistance - lightly thixotropic - semi-film former.

RECOMMENDED USES

Protective and decorative finishing of interior and exterior woodwork.

TECHNICAL DATA

Appearance:	Semi-gloss (gloss 60°: ± 40% on wood)
Colour:	9 wood tints (see colour chart)
Density:	0,89 - 0,93 g/cm ³
Solids Content:	In volume: ± 42% In weight: ± 50%
Recommended film thickness:	Wet film: ± 100 micron (cons.: 10 m ² /l) Dry film: ± 42 micron (cons.: 10 m ² /l)
VOC-content:	Max. 470 g/l
Flashpoint:	> 39°C

Drying times 20°C/50% r.h.

To touch:	± 6 hours (15 m ² /l)
To handle:	± 7 hours (15 m ² /l)
To recoat:	1 day
Full hardness	± 1 week

Coverage

Theoretical:	± 10 - 15 m ² /l per coat
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Apply on Fassitek.

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit, Afzelia with ammonia water.

Old stripped paint: rub down up to the bare not impregnated wood fibre and make dust free.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush:	By preference, apply undiluted.
Roller:	By preference, apply undiluted.
Air-atomised spray:	By preference, apply undiluted.
Airless spray:	By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars
Cleanup:	White spirit or Thinner 22

PRODUCT DATA

FASSITOP

APPLICATION CONDITIONS

Apply in a dry and well-ventilated area.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk