

PRODUCT DATA

FIXONAL

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Fixing agent based on solvent soluble pure acrylic resins.

MAIN PROPERTIES

Fixing and reinforcing - alkali resistant - quick drying - flexible.

RECOMMENDED USES

Fixation of chalking substrates.

Reinforces the adhesion of the new coat on the old paint and makes more flexible.

TECHNICAL DATA

Appearance:	Gloss (gloss 60°: > 90%)
Colour:	Colourless
Density:	0,81 - 0,83 g/cm ³
Solids Content:	In volume: ± 15%
	In weight: ± 19%
Recommended film thickness:	Wet film: ± 100 micron (cons.: 10 m ² /l)
	Dry film: ± 15 micron (cons.: 10 m ² /l)
Flashpoint:	> 39°C
VOC-content:	700 g/l max.
Ready-for-use mixture:	700 g/l max.
Category:	A/h
EU Limit values:	750 g/l (2007) / 750 g/l (2010)

Drying times 20°C/50% r.h.

To touch: ± 45 minutes

To handle: ± 1 hour

To recoat: ± 2 - 4 hours

Full hardness: ± 1 day

Coverage

Theoretical: ±10 - 15 m²/l, according to the porosity of the substrate.

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The surfaces to be treated must be dry, clean and adhering. Chalking substrates must be rubbed down with a hard brush and dusted off. Rub down glossy coats. Degrease if necessary. After drying, apply the topcoat as quickly as possible.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush: By preference, do not dilute.

Roller: By preference, do not dilute.

Air-atomised spray: Not recommended

Airless spray: Not recommended

PRODUCT DATA

FIXONAL

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

Cleanup: White spirit

APPLICATION CONDITIONS

Work in a dry and well-ventilated area.

REMARKS

Fixonal does not improve the adhesion of old paint coats on the substrate.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.