

## PRODUCT DATA

## METAL CLADDING TOPCOAT

### DESCRIPTION

Waterborne semi-gloss acrylic paint specially designed for use as a finish on metal cladding primed with MATHYS® Metal Cladding Primer or on any metal surface coated with NOXYDE® or PEGANOX®.

### MAIN PROPERTIES

Very decorative semi-gloss aspect - easy to clean and to maintain - high filling and hiding power - excellent flow out - high durability and gloss stability - unsaponifiable.

### RECOMMENDED USES

Finish on metal cladding primed with MATHYS® Metal Cladding Primer or on any metal surface coated with NOXYDE® or PEGANOX® (incl. metal cladding).

### TECHNICAL DATA

Appearance:	Semi-gloss (gloss 60°: ± 65%)
Colour:	Base P – Base TR – Base D
Density:	1,28 – 1,32 g/cm <sup>3</sup>
Solids Content:	In volume: 35 - 38% In weight: 50 - 53%
Recommended film thickness:	Wet film: ± 125 micron (cons.: 8 m <sup>2</sup> /l) Dry film: ± 45 micron (cons.: 8 m <sup>2</sup> /l)
Flashpoint:	Not flammable
VOC-content:	15 g/l max.
Ready-for-use mixture:	15 g/l max.
Category:	A/c
EU Limit values:	75 g/l (2007) / 40 g/l (2010)

<b>Drying times</b>	20°C/50% r.h.
To touch:	40 minutes (10 m <sup>2</sup> /l)
To handle:	2 hours (10 m <sup>2</sup> /l)
To recoat:	4 hours (10 m <sup>2</sup> /l)
Full hardness:	± 1 day

### Coverage

Theoretical:	8 - 10 m <sup>2</sup> /l
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

### SURFACE PREPARATION

Can be applied directly on substrates primed with MATHYS® Metal Cladding Primer, NOXYDE® or PEGANOX®.

Can also be applied on old sound paints; glossy paints will be roughed up slightly.

In all cases, the substrate must be sufficiently dry and clean.

Apply 1 - 2 coats of the Metal Cladding Topcoat.

### DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

### APPLICATION & THINNING

Brush: Apply in 2 coats by preference. If necessary dilute with water.

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk

**PRODUCT DATA**

**METAL CLADDING TOPCOAT**

Roller: Apply in 2 coats by preference. Use short nap roller. If necessary dilute with water.

Air-atomised spray: Not recommended.

Airless spray: Nozzle: 018 / Pressure: 180 bars. 1 coat is sufficient in most cases. If necessary dilute with water.

Cleanup: Water

**APPLICATION CONDITIONS**

Temperature min. 5°C / max. 80 % R.H.

**REMARKS**

The product can remain a little sticky if it is used on new cladding.

**SAFETY**

Consult Safety Data Sheet and Safety Information printed on the can.

**SHELLIFE / STORAGE CONDITIONS**

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

[info@mathysdirect.co.uk](mailto:info@mathysdirect.co.uk)  
[www.mathysdirect.co.uk](http://www.mathysdirect.co.uk)