

PRODUCT DATA

MURFILL FLEECE (non woven)

DESCRIPTION

Polyester fibres woven in hexagonal meshes.

RECOMMENDED USES

Reinforcement of the first coat of Dakfill New for the system Dakfill-Waterproofing.

TECHNICAL DATA (according to the data given by the manufacturer)

| | | |
|----------------------------|-------------|---|
| Composition | : | 100% polyester fibres |
| Quality | : | Flexible |
| Weight | : | 48 - 52 g/m ² |
| Thickness | : | 0,28 - 0,29 mm |
| Traction force in N/5 cm | By warp | : ± 140 |
| | By weft | : ± 95 |
| GRAB elongation in % | By warp | : ± 29 |
| | By weft | : ± 260 |
| Resistance to | UV | : Good - behind glass 7 to 10 years |
| | Temperature | : Good |
| | Acids | : In 50% of sulphuric acid - room temperature - 6 months. |
| | Alkali | : Good - only the surface of the fibres will be attacked at room temperature. |
| Thermal retraction at 40°C | By warp | : ± 3 |
| | By weft | : ± 1,7% |
| Dimensions | Widths | : 20 cm, 60 cm en 100 cm |
| | Roll length | : 100 m |
| Tolerances | Width | : Geen |
| | Length | : - 0 m + 1 m |

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk