

**PRODUCT DATA**

**MURFILL MESH (woven)**

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk

**DESCRIPTION**

Polyamide fibres woven in block meshes.

**RECOMMENDED USES**

Reinforcement of the first coat of the Murfill waterproofing system on structural surfaces.

**TECHNICAL DATA** (according to the data given by the manufacturer)

Composition	:	100% polyamide fibres
Quality	:	Woven
Weight	:	48 - 52 g/m <sup>2</sup>
Thickness	:	0,27 - 0,30 mm
Traction force in N/5 cm	By warp	: ± 250
	By weft	: ± 220
GRAB elongation in %	By warp	: ± 60
	By weft	: ± 140
Resistance to	UV	: Reasonably good
	Temperature	: Good
	Acids	: Good
	Alkali	: Good
Thermal retraction at 40°C	By warp	: - 10%
	By weft	: - 8%
Dimensions	Widths	: 16 cm and 100 cm
	Roll length	: 100 m
Tolerances	Width	: None
	Length	: - 0 m + 1 m