

PRODUCT DATA ALKALINE CLEANER/DEGREASER ND 14

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

RUST-OLEUM® Alkaline Cleaner/Degreaser ND 14 is a concentrated, alkaline, non-flammable, virtually odour-free cleaning/degreasing solution.

RECOMMENDED USES

RUST-OLEUM Alkaline Cleaner/Degreaser ND 14 should be used to remove grease, oil, proteins dirt and many other surface contaminants from coated, mineral and steel substrates. RUST-OLEUM Alkaline Cleaner/Degreaser ND 14 should be applied with an artificial sponge, cloth or stiff nylon brush or broom. RUST-OLEUM Alkaline Cleaner/Degreaser ND 14 can also be used as an additive for high-pressure (steam) cleaning.

TECHNICAL DATA

VOC-content: 92 g/l

Coverage

Theoretical: 6 - 8 m²/l
Practical: Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

DIRECTION FOR USE

To ensure homogeneity shake well before use.
Scrape or sweep away grease, oil, dirt, mould and all other surface contaminations as much as possible.
RUST-OLEUM Alkaline Cleaner/Degreaser ND 14 can be applied diluted or concentrated with a sponge, cloth, brush or broom. For normal cleaning a 3 - 5% concentration will be sufficient. The product should be diluted with cold water. After use rinse with plenty of fresh water. If a concentration of more than 5% is used, hot water rinsing is absolutely necessary. As a high-pressure(steam) cleaning additive a 2% concentration is recommended. After cleaning, remove any remaining water and allow the surface to dry, as moisture left on the surface or entrapped into pores may cause premature failure of the coating system. Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

APPLICATION CONDITIONS

Temperature of air, substrate and material between 5 and 35°C.

REMARKS

If used on galvanized steel, zinc, aluminum or anodized aluminum rinse the surface excessively.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.