

PRODUCT DATA

NOXYDE MESH

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Polyester fibres woven in hexagonal meshes.

RECOMMENDED USES

Reinforcement of the first coat of Noxyde on balconies.

TECHNICAL DATA (according to the data given by the manufacturer)

Composition	:	100% polyester fibres
Quality	:	Stiff
Weight	:	48 - 52 g/m ²
Thickness	:	0,28 - 0,29 mm
Traction force in N/5 cm	By warp	: ± 140
	By weft	: ± 95
GRAB elongation in %	By warp	: ± 29
	By weft	: ± 260
Resistance to	UV	: Good - behind glass 7 to 10 years
	Temperature	: Good
	Acids	: In 50% of sulphuric acid - room temperature - 6 months
	Alkali	: Good - only the surface of the fibres will be attacked at room temperature
Thermal retraction at 40°C	By warp	: - 3%
	By weft	: - 1.7%
Dimensions	Widths	: 60 cm and 120 cm
	Roll length	: 100 m
Tolerances	Width	: None
	Length	: - 0 m + 1 m