

PRODUCT DATA

PARACEM DECO PLAFOND

DESCRIPTION

Waterborne one-coat acrylic paint.

MAIN PROPERTIES

Exceptional high covering capacity (covers mostly in 1 coat) - uniform matt finish without laps - delayed drying (enables to carry out large surfaces) - odourless - extra matt - easy application.

RECOMMENDED USES

For indoor walls and ceilings: on plaster, plasterboard, rendering, bricks, concrete etc. as well as on old paints, wallpaper, ingrain wallpaper, etc.

TECHNICAL DATA

Appearance:	Matt (gloss 60°: 2%)
Colour:	White + ColourShop / Mathymix Base P
Density:	1.41 - 1.45 g/cm ³
Solids Content:	In volume: 32 - 34% In weight: 52 - 54%
Recommended film thickness:	Wet film: ± 140 micron (consumption: 7 m ² /l) Dry film: ± 45 micron (consumption: 7 m ² /l)
Flashpoint:	Not flammable
VOC-content:	28 g/l max.
Ready-for-use mixture:	29 g/l max.
Category:	A/a
EU Limit values:	70 g/l (2007) / 30 g/l (2010)

Drying times 20°C/50% r.h.

To touch: 2 hours

To recoat: 4 hours

Full hardness: ± 1 day

Coverage

Theoretical: 6 - 8 m²/l

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Always work on a dry and stable substrate.

Old cleaned layers in good condition and light porous substrates may be recoated directly with Paracem Deco Plafond.

Very porous substrates, smooth plaster and water-resistant plasterboard are to be impregnated first with Pegafix.

Nicotine stains must be isolated first with Pegaprim Isofix, Pegamat Aqua or Pegamat RL.

Old damp spots must be isolated with Pegamat RL or Pegaprim Isofix.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim or Pegaprim Xpress).

Metal objects without rust spots are to be pre-treated with Pegalink, Pegaprim Xpress or Galvaprim.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

PRODUCT DATA

PARACEM DECO PLAFOND

APPLICATION & THINNING

Brush:	Apply undiluted.
Roller:	Apply undiluted.
Air-atomised spray:	Not recommended.
Airless spray:	If necessary, dilute with some water. Nozzle: 011 - 013 / Pressure: 200 bars.
Cleanup:	Water.

APPLICATION CONDITIONS

Minimum 5°C / Maximum 80% R.H.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk