

## PRODUCT DATA

## Paracem Deco Premium Mat

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk

### DESCRIPTION

Water based flat insulating paint with a good hiding for use on interior walls and ceilings based on modified alkyd resins.

### MAIN PROPERTIES

High covering power - insulates stains and colours (nicotine stains, old damp spots, soot stains, etc.) - low odour - low tension film - primer and topcoat in one - uniform flat aspect - long open time.

### RECOMMENDED USES

Insulating paints for interior walls and ceilings.

### TECHNICAL DATA

Appearance:	Flat (gloss 85°: 2%)
Colour:	White + off-white colours with Mathymix (base P + M)
Density:	1,45 - 1,51 g/cm <sup>3</sup>
Solids Content:	In volume: 38 - 42% (white) In weight: 58 - 62% (white)
Recommended film thickness:	Wet film: ± 140 micron (consumption: 7 m <sup>2</sup> /l) Dry film: ± 56 micron (consumption: 7 m <sup>2</sup> /l)
Flashpoint:	Not flammable
VOC-content:	53 g/l max.
Ready-for-use mixture:	53 g/l max.
Category:	A/i
EU Limit values:	140 g/l (2007) / 140 g/l (2010)

### Drying times 20°C/50% r.h.

To touch:	1 hour
To recoat:	2 hours
Full hardness:	± 2 days

### Coverage

Theoretical:	7 m <sup>2</sup> /l per coat
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

### SURFACE PREPARATION

Apply on a dry and sound substrate.

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc.

On very absorbent substrates (not painted), apply an impregnation coat of Pegafix.

On substrates with nicotine spots: first clean these with an ammonia solution in order to receive a better efficiency of the paint.

Apply 1 or 2 coats according to the condition of the substrate.

Can be applied on completely dry Elastofill/Pegaflex without the risk of crack formation.

### DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PRODUCT DATA

## Paracem Deco Premium Mat

### APPLICATION & THINNING

- Brush: Apply undiluted.
- Roller: Apply undiluted.
- Air-atomised spray: If necessary, dilute with a little water.
- Airless spray: Nozzle: 011 - 013 / Pressure: 180 bar  
If necessary, dilute with a little water.
- Cleanup: Water.

### APPLICATION CONDITIONS

> 5°C and < 80% R.H.

### REMARKS

- Can be recoated with all water-based paint, and also with Pegamat RL.
- Can be applied directly on Pegamat RL, Pegaprim Isofix and Pegaprim Express.
- In case of old damp spots or colour marks, apply first a test patch. When insufficient insulation properties, use Pegamat RL or Pegaprim Isofix.

### SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

### SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk