

## PRODUCT DATA

## PARACEM DECO SOFT

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk

### DESCRIPTION

Waterborne acrylic paint for high-quality indoor works.

### MAIN PROPERTIES

Excellent flow - excellent mechanical resistance against rubbing - smooth satin matt aspect - closed coating structure - washable - high covering power - tendency not to overlap.

### RECOMMENDED USES

Decorative and satin matt finishing for indoor walls and ceilings.  
Applicable on most substrates (plaster, bricks, concrete, etc.) as well on glass fibre.

### TECHNICAL DATA

Appearance:	Satin matt (gloss 60°: 5 - 8% / 85°: 15 - 20%)
Colour:	White + Mathymix / ColourShop
Density:	1,40 – 1,44 g/cm <sup>3</sup> (white)
Solids Content:	In volume: 35 ± 1% (white) In weight: 55 ± 1% (white)
Recommended film thickness:	Wet film: ± 140 micron (consumption: 7 m <sup>2</sup> /l) Dry film: ± 50 micron (consumption: 7 m <sup>2</sup> /l)
Flashpoint:	Not flammable
VOC-content:	15 g/l max.
Ready-for-use mixture:	< 30 g/l max.
Category:	A/a
EU Limit values:	75 g/l (2007) / 30 g/l (2010)

**Drying times** 20°C/50% r.h.

To touch:	1 hour
To recoat:	2 hours
Full hardness	± 2 days

### Coverage

Theoretical:	7 - 9 m <sup>2</sup> /l per coat
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

### SURFACE PREPARATION

Old cleaned layers in good condition and light porous substrates may be recoated directly with Paracem Deco Soft.

Very porous substrates, smooth plaster and water-resistant plasterboard are to be impregnated first with Pegafix.

Nicotine stains must be isolated first with Pegaprim Isofix, Pegamat Aqua or Pegamat RL.

Old damp spots must be isolated with Pegamat RL or Pegaprim Isofix.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim or Pegaprim Xpress).

Metal objects without rust spots are to be pre-treated with Pegalink, Pegaprim Xpress or Galvaprim.

### DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PRODUCT DATA

## PARACEM DECO SOFT

### APPLICATION & THINNING

- Brush: Apply undiluted.
- Roller: Apply undiluted.
- Air-atomised spray: Dilute, if necessary with water.
- Airless spray: Nozzle: 013 - 019 / Pressure: 160 - 200 bars.
- Cleanup: Water.

### APPLICATION CONDITIONS

> 5°C, < 80% R.H.

### SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

### SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

[info@mathysdirect.co.uk](mailto:info@mathysdirect.co.uk)  
[www.mathysdirect.co.uk](http://www.mathysdirect.co.uk)