

PRODUCT DATA

PARACEM EFFECTS PRIMER

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

White primer based on acrylic dispersions.

MAIN PROPERTIES

Reinforces the substrate and decreases the absorption.

RECOMMENDED USES

For interior applications, on different porous non-painted surfaces (e.g. bricks, plaster, concrete) before painting them with Paracem Effects.

TECHNICAL DATA

| | |
|-----------------------------|---|
| Appearance: | Matt (gloss 60°: ± 5%) |
| Colour: | White |
| Density: | ± 1,27 g/cm ³ |
| Solids Content: | In volume: 26 - 27% In weight: 41 - 43% |
| Recommended film thickness: | Wet film: 100 micron (consumption: 10 m ² /l) Dry film: 28 micron (consumption: 10 m ² /l) |
| Flashpoint: | Not flammable |
| VOC-content: | 29 g/l max. |
| Ready-for-use mixture: | 29 g/l max. |
| Category: | A/g |
| EU Limit values: | 50 g/l (2007) / 30 g/l (2010) |

Drying times 20°C/50% r.h.

| | |
|---------------|-------------|
| To touch: | 1½ hours |
| To recoat: | 2 - 3 hours |
| Full hardness | 1 week |

Coverage

| | |
|--------------|--|
| Theoretical: | ± 8 m ² /l |
| Practical: | Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application. |

SURFACE PREPARATION

The substrate must be clean and degreased.

Very porous substrates, smooth plaster and water-resistant plasterboard are to be impregnated first with a coat of Pegafix.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

| | |
|---------------------|---|
| Brush: | Apply undiluted. |
| Roller: | Apply undiluted. |
| Air-atomised spray: | Apply undiluted. |
| Airless spray: | Apply undiluted. Nozzle: 011 - 015 / Pressure: 180 - 200 bars. |
| Cleanup: | Water. |

PRODUCT DATA

PARACEM EFFECTS PRIMER

APPLICATION CONDITIONS

Apply at a temperature of at least 5°C and maximum 80% R.H.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk