

PRODUCT DATA

PARACEM EFFECTS SAND/SABLE

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Waterborne acrylic paint with fine sand structure for application on interior walls.

MAIN PROPERTIES

Long open time (2 – 3 hours) - no tendency to overlap - splash free - good hiding power - odourless - closed coating structure - homogeneous diffusion of the sand in the paint without sedimentation in the can.

RECOMMENDED USES

Aesthetical embellishment of most common interior substrates (plaster, bricks, concrete); also applicable on glass fibre.

TECHNICAL DATA

Appearance:	Fine sand structure
Colour:	Tinting machine colours: base P + base TR
Density:	± 1,3 - 1,4 g/cm ³
Solids Content:	In volume: ± 30%
	In weight: ± 48%
Recommended film thickness:	Wet film: ± 90 micron (consumption: 8 m ² /kg)
	Dry film: ± 27 micron (consumption: 8 m ² /kg)
Flashpoint:	Not flammable
VOC-content:	179 g/l max.
Ready-for-use mixture:	179 g/l max.
Category:	A/i
EU Limit values:	300 g/l (2007) / 200 g/l (2010)

Drying times 20°C/50% r.h.

To touch:	4 hours
To recoat:	24 hours
Full hardness:	± 1 day

Coverage

Theoretical:	± 8 m ² /kg
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Walls in bad condition: Eliminate carefully the old paint or non-adherent plaster; sanding with metallic brush. Large repairs to be performed with cement mixture or Pegacrete. Small repairs to be performed with a mixture of Paracem Quartz and fine sand. After drying, these repairs shall be primed with Pegafix. Seal joints and fissures with Elastofill.

Old cleaned paint coats in good condition and slightly porous substrates can be repainted immediately with Paracem Effects Sand / Sable. Porous substrates must be impregnated first with Paracem Effects Primer. Damp spots or nicotine stains are to be isolated with Pegaprim Isofix or Pegamat RL.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PRODUCT DATA

PARACEM EFFECTS SAND/SABLE

APPLICATION & THINNING

Brush: Apply with Paracem Effects brush in cross movements. If necessary, dilute with water.

Cleanup: Water.

APPLICATION CONDITIONS

Min. 5°C / max. 80% R.H.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk