

PRODUCT DATA

PARAFIX

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Colourless fixation primer based on acrylic dispersions for weathered bituminous substrates.

RECOMMENDED USES

Fixation coat on weathered bituminous surfaces before recoating with Dacfill, Dacfill HZ or Dac-Hydro-Alu.

TECHNICAL DATA

Appearance:	Glossy (gloss 60°: ± 90%)
Colour:	Colourless
Density:	1,0 g/cm ³
Solids Content:	In volume: 27 - 29% In weight: 27 - 29%
Recommended film thickness:	Wet film: 100 micron (cons.: 10 m ² /l) Dry film: 28 micron (cons.: 10 m ² /l)
Flashpoint:	Not flammable
VOC-content:	40 g/l max.
Ready-for-use mixture:	40 g/l max.
Category:	A/i
EU Limit values:	140 g/l (2007) / 140 g/l (2010)

Drying times 20°C/50% r.h.

To touch:	1½ hours
To handle:	4 hours
To recoat:	1 day
Full hardness	1 week

Coverage

Theoretical:	5 - 10 m ² /l
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Do not apply on fibre cement boards: use Primer 44 HS in this case.
Do not apply on low porous substrates like plaster, use Pegafix in this case.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush:	Apply undiluted.
Roller:	Apply undiluted.
Air-atomised spray:	Dilute with water.
Airless spray:	Apply undiluted. Nozzle: 011 - 015 / Pressure: 180 - 200 bars
Cleanup:	Water

PRODUCT DATA

PARAFIX

APPLICATION CONDITIONS

Minimum 5°C - Maximum 80 % R.H.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk