

PRODUCT DATA

PEGAMAT AQUA

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Water based insulating paint based on modified alkyd resins.

MAIN PROPERTIES

High covering power - low odour - low tension film - uniform flat film - insulates nicotine and soot stains, old damp spots and several colour marks - also suitable for insulating hard foam boards, like polystyrene - long open time.

RECOMMENDED USES

Renovation paint for interior walls and ceilings.

TECHNICAL DATA

Appearance:	Flat (gloss 60°: 2%)
Colour:	White + off-white colours with Mathymix (base P + M)
Density:	1,50 - 1,55 g/cm ³
Solids Content:	In volume: 41 - 44% (white) In weight: 62 - 64% (white)
Recommended film thickness:	Wet film: ± 140 micron (consumption: 7 m ² /l) Dry film: ± 60 micron (consumption: 7 m ² /l)
Flashpoint:	Not flammable
VOC-content:	65 g/l max.
Ready-for-use mixture:	65 g/l max.
Category:	A/i
EU Limit values:	140 g/l (2007) / 140 g/l (2010)

Drying times 20°C/50% r.h.

To touch:	1 hour
To recoat:	2 hours
Full hardness:	± 2 days

Coverage

Theoretical:	6 - 8 m ² /l per coat
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Apply on a dry and sound substrate.

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc.

On very absorbent substrates (not painted), apply an impregnation coat of Pegafix.

On substrates with nicotine spots: first clean these with an ammonia solution in order to receive a better efficiency of the paint.

Apply 1 or 2 coats according to the condition of the substrate.

Can be applied on completely dry Elastofill / Pegaflex without the risk of crack formation.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush: Apply undiluted.

Roller: Apply undiluted.

PRODUCT DATA

PEGAMAT AQUA

Air-atomised spray: If necessary, dilute with a little water.

Airless spray: Nozzle: 011 - 013 / Pressure: 180 bar
If necessary, dilute with a little water.

Cleanup: Water.

APPLICATION CONDITIONS

> 5°C and < 80% R.H.

REMARKS

- If a darker finish is requested, apply Paracem Deco or Paracem Deco Satin.
- Can be recoated with all water-based paint, and also with Pegamat RL.
- Can be applied directly on Pegamat RL.
- In case of old damp spots or colour marks, apply a test patch. When insufficient insulation properties, use Pegamat RL.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk