

PRODUCT DATA

PEGAMAT RL

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Deodorised solvent-based enamel based on plastified acrylic resins.

MAIN PROPERTIES

High covering power - non yellowing - low tension film - unsaponifiable - matt film without laps - isolates nicotine stains, old damp spots and several colouring matters - also suitable for insulating hard foam boards, even those in polystyrene.

RECOMMENDED USES

Renovation paint for interior walls and ceilings.

TECHNICAL DATA

Appearance:	Matt (gloss 60°: < 2%)
Colour:	White
Density:	1,33 - 1,37 g/cm ³
Solids Content:	In volume: 38 - 40%
	In weight: 64 - 66%
Recommended film thickness:	Wet film: ± 100 micron (cons.: 10 m ² /l)
	Dry film: ± 40 micron (cons.: 10 m ² /l)
Flashpoint:	62°C
VOC-content:	455 g/l max.
Ready-for-use mixture:	485 g/l max.
Category:	A/i
EU Limit values:	600 g/l (2007) / 500 g/l (2010)

Drying times	20°C/50% r.h.
To touch:	3 hours
To recoat:	Wet in wet or after 4 hours
Full hardness:	± 1 day

Coverage

Theoretical:	9 - 12 m ² /l per coat
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc. Mostly it is not necessary to clean them first, but they should be sufficiently dry and stable, however. Apply 1 or 2 coats according to the condition of the substrate; if necessary, the second coat can be applied wet in wet. Do not apply on Elastofill; when using Pegaflex, it must first be insulated with Porisol.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush:	Dilute with 3-5% Thinner RL or White spirit if necessary.
Roller:	Dilute with 3-5% Thinner RL or White spirit if necessary.
Air-atomised spray:	Possible.

PRODUCT DATA

PEGAMAT RL

Airless spray: Nozzle: 011 - 015 / Pressure: 180 bars
Dilute max. 5% with Thinner RL or White spirit if necessary.

Cleanup: White spirit.

APPLICATION CONDITIONS

Apply in a dry and well-ventilated area.

REMARKS

White spirit increases the odour and makes its use impossible on polystyrene foam. Pegamat is a reversible paint system, this means that it dissolves in its own solvent. Therefore, dried spots of Pegamat can be removed with Thinner RL or white spirit. Do not tint with universal pigments or on the tinting machine. For pastel shades, you can tint with max. 5% Fassilux Satin (3% for black).

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk