

## PRODUCT DATA

## PEGAPRIM SANITOP

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk

### DESCRIPTION

Anti-mildew paint based on waterborne acrylic resins.

### MAIN PROPERTIES

High durability - excellent saponification resistance - high covering capacity - fungicidal - flexible - excellent adhesion.

### RECOMMENDED USES

For the interior coating of humid sensitive areas where mildew can grow.  
As durable interior / exterior coating on mineral substrates (masonry, plaster, concrete, bricks) with enhanced fungicidal protection.

### TECHNICAL DATA

Appearance:	Satin matt (gloss 60°: ± 5%)
Colour:	White + base P
Density:	± 1.4 g/cm <sup>3</sup>
Solids Content:	In volume: 47 - 50% In weight: 62 - 65%
Recommended film thickness:	Wet film: ± 125 micron (consumption: 8 m <sup>2</sup> /l) Dry film: ± 60 micron (consumption: 8 m <sup>2</sup> /l)
Flashpoint:	Not flammable
VOC-content:	23 g/l max.
Ready-for-use mixture:	23 g/l max.
Category:	A/i
EU Limit values:	140 g/l (2007) / 140 g/l (2010)

<b>Drying times</b>	20°C/50% r.h.
To touch:	± 40 minutes (10 m <sup>2</sup> /l)
To recoat:	± 4 hours (10 m <sup>2</sup> /l)
Full hardness	± 1 day

### Coverage

Theoretical:	7 - 10 m <sup>2</sup> /l per coat
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

### SURFACE PREPARATION

The substrate must be sufficiently dry and stable; clean thoroughly.  
On porous substrates apply first a coat of diluted Pegaprim Xpress, or preferably a coat of Pegafix.  
On smooth bricks, apply a first coat of Pegaprim Xpress.  
Impregnate old chalking paints, after cleaning, with a coat of Fixonal or Pegafix.  
Fill up holes and seal joints or fissures with Elastofill or Biosan Sealant. If necessary, equalise with Pegaflex. Flat down and remove dust. Hereafter, apply 1 - 2 coats of Pegaprim Sanitop.

### DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

### APPLICATION & THINNING

Brush: Apply with flat brush. If necessary, dilute with 5% of water or Fair-Décor (for a longer drying time).

## PRODUCT DATA

## PEGAPRIM SANITOP

Roller:	Apply with flat brush. If necessary, dilute with 5% of water or Fair-Decor (for a longer drying time).
Air-atomised spray:	Dilute with water (3 - 5%).
Airless spray:	Nozzle: 013 - 018 / Pressure: 180 bars
Cleanup:	Water.

### APPLICATION CONDITIONS

Minimum 5°C / Maximum 80% R.H.

### SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

### SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk