

PRODUCT DATA

PEGATEX NEW

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk

DESCRIPTION

Latex paint for interior and exterior protection

MAIN PROPERTIES

Mat appearance, easy cleanability, easy to apply, good hiding

RECOMMENDED USES

Inner walls: plaster, rendering, panels fibre cement, Gyproc.

Exterior walls: bricks, all kinds of construction materials excepted new ones less than 2 years old.

TECHNICAL DATA

Appearance:	Mat 2 (°60)
Colour:	White and Mathymix
Density:	+/- 1.4 g/cm ³
Solids Content:	In volume: +/- 38 % In weight: +/- 55 %
Recommended film thickness:	Wet film: 100 µm (10 m ² /l) Dry film: 37 µm (10 m ² /l)
Flashpoint:	Not flammable
VOC-content:	20 g/l max.
Ready to use mixture:	29,8 g/l max.
Category:	A/a
EU Limit values:	75 g/l (2007) / 30 g/l (2010)

Drying times 20°C/50% r.h.

To touch:	1 hour
To handle:	5 hours
To recoat:	After 4 hours
Full hardness	+/- 1 day

Coverage

Theoretical: 8-10 m²/l per layer

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Application on not alkaline substrates in good state.

Interior: porous surfaces to prime with Pegafix or with a first coat diluted with 10% water.

Exterior: Not painted substrates to prime with Pegafix.

DIRECTION FOR USE

Before application, stir the product till complete homogenous.

APPLICATION & THINNING

Brush: Do not dilute

Roller: Do not dilute

Air-atomised spray: If necessary, dilute with water

PRODUCT DATA

PEGATEX NEW

Airless spray: If necessary, dilute with water.
Nozzle: 013/ Pressure: 180 bar.

Cleanup: Water

APPLICATION CONDITIONS

Minimum 5°C en maximum 80 % RH

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@mathysdirect.co.uk
www.mathysdirect.co.uk