

# Technical information 2

## COATING PRIMER

Product/Series	Description	Comp.	Inside use Outside use	Resin type	WB / SB	Appearance	Coverage	Solids volume % (depending on colour)	Recommended dry film thickness	VOC contents	Application temperature / Relative humidity	To touch	To handle (light traffic)	To recoat	Fully cured	Application tools	Colours	Heat-resistance - dry heat	Thinner	Page nr.
COATING PRT®	Solvent based acrylic paint	1-pack	•	Acrylic	Solvent based	Satin gloss	6-8 m²/l.	41-43%	60 µm	532 gr/l	5-35°C	3 hrs	4 hrs	24 hrs	24 hrs	Brush, Roller, Spray	White, grey, black	-	-	56
COATING PRT® - RAPID SUPER	Aluminium roof paint	1-pack	•	Acrylic	Solvent based	Glossy	13 m²/l.	30-32%	25 µm	585 gr/l	5-35°C	1.5 hrs	2 hrs	-	24 hrs	Brush, Roller, Spray	Aluminium	-	-	51
DACFILL HZ	Water based roof coating for horizontal roofs	2-pack	•	Acrylic	Water based	Satin-matt	1-1,5 kg./m²	51%	600 µm	55 gr/l	>5°C RH:<85%	1.5 hrs	2.5 hrs	overnight	1 week	Brush, Roller, Spray	Grey	-	-	50
DACFILL SB EMBEDMENT	Solvent based undercoat for roofs	1-pack	•	Urethane	Solvent based	Low sheen	1-2 m²/l.	78%	0.5-1.0 mm	284 gr/l	>5°C	4 hrs	-	12 hrs - 5 days	12 hrs.	Brush, Roller, Spray	Deep pink	-	-	49
DACFILL SB TOPCOAT	Solvent based topcoat for roofs	1-pack	•	Urethane	Solvent based	Semi gloss	1-2 m²/l.	80%	0.4-0.8 mm	262 gr/l	>5°C	4 hrs	-	12hrs-7 days	16 hrs.	Brush, Roller, Spray	Dove grey	-	-	49
DACFILL	Water based roof coating for sloped roofs	1-pack	•	Acrylic	Water based	Matt	0,6-3 kg./m²	57-60%	600 µm	5 gr/l	>5°C RH:<80%	2 hrs	6 hrs	24 hrs	1 hr.	Brush, Roller, Spray	See colour card	-	Water	48
DAC-HYDRO-ALU	Aluminium roof paint	1-pack	•	Acrylic	Water based	Glossy	Waterproofing: 1-1.5 L/m² esthetical: 0.3-0.5 L/m²	47-49%	480 µm	70 gr/l	>5°C	4 hrs	6-7 hrs	24 hrs	1 week	Brush, Roller, Spray	Aluminium	-	-	51
DAC HYDRO-D	Water based roof tile paint	1-pack	•	Acrylic	Water based	Satin-matt	6-8 m²/l.	42%	70 µm	40 gr/l	>8°C RH:<80%	1 hr	2 hrs	24 hrs	1 week	Brush, Roller, Spray	See colour card	-	-	54
DAC HYDRO PLUS	Water based roof tile paint	1-pack	•	Acrylic	Water based	Matt	9-11 m²/l.	30%	33 µm	35 gr/l	>8°C RH:<80%	1 hr	2 hrs	24 hrs	1 week	Brush, Roller, Spray	See colour card	-	-	55
DAKFILL FRIGO	Gas & vapour tight coating	1-pack	•	Acrylic	Water based	Satin-matt	Repair: 0.5-1 L/m² Repair: 2-3 L/m²	53-57%	380 µm	35 gr/l	>5°C RH:<85%	1.5 hrs	-	24 hrs	1 week	Brush, Roller, Spray	White	-	-	61
DURBOCEM®	Paint for damp walls & cellars	1-pack	•	Acrylic	Solvent based	Matt	1.5-3 m²/l.	38-40%	200 µm	500 gr/l	5-35°C	2 hrs	2 hrs	24 hrs	24 hrs	Brush, Roller	White/ColourShop	-	-	45
DK20 S PAINT STRIPPER	Highly effective paint stripper	1-pack	•	-	-	-	2-4 m²/l.	-	-	110 gr/l	-	-	-	-	-	Brush	-	-	-	-
ELASTOFILL®	Elastic jointing paste	1-pack	•	Acrylic	Water based	Satin gloss	10mm. x 15mm. x 6m.	64-67%	6.5 mm	5 gr/l	>5°C RH:<80%	3 hrs	8 hrs	24 hrs	1 week	Cartridge/glue spreader	See colour card	-	-	26
FASSICLOR®	Solvent borne chlorinated rubber paint	1-pack	•	Chlorinated rubber	Solvent based	Satin gloss	2 coats of 6 m²/l.	28-33%	50 µm	640 gr/l	5-35°C	1.5 hrs	3 hrs	24 hrs	12 days	Brush, Roller, Spray	See colour card	-	Thinner 22	-
FILLCOAT® FIBRES	Instant waterproofing coating (fibres reinforced)	1-pack	•	High polymers	Solvent based	Fibre structure	1.5 l/m²	41-43%	430 µm	485 gr/l	5-35°C	4 hrs	-	3-14 days	-	Brush, Roller	Light and dark grey	-	-	53
FILLCOAT®	Instant waterproofing coating	1-pack	•	High polymers	Solvent based	Satin gloss	1 - 1.5 l/m²	42-44%	430 µm	486 gr/l	5-35°C	4 hrs	-	3-14 days	-	Brush, Roller	Light and dark grey, black	-	-	53
FK111 Mould remover	Mould removing cleaning solution	1-pack	•	-	-	-	6-8 m²/l.	-	-	0 gr/l	5-35°C	-	-	-	-	Brush	-	-	-	-
ND14 Cleaner/Degreaser	Alkaline cleaner/degreaser	1-pack	•	-	Solvent based	-	6-8 m²/l.	-	-	92 gr/l	5-35°C	-	-	-	-	Sponge, Brush, Broom	-	-	Water	38
MURFILL® WATERPROOFING	Elastic waterproofing coating	1-pack	•	High polymers	Water based	Satin matt	300-600 g/m²	47-50%	140 µm	40 gr/l	>5°C RH:<80%	45 min	8 hrs	24 hrs	48 hrs	Brush, Roller, Spray	White/ColourShop	-	Water	42
MURFILL® RENOVATION	Elastic renovation coating	1-pack	•	High polymers	Water based	Matt	400 g/m²	47-50%	70 µm	30 gr/l	>5°C RH:<80%	45 min	8 hrs	24 hrs	48 hrs	Brush, Roller, Spray	White/ColourShop	-	Water	43
MURFILL® QUARTZ	Elastic waterproofing Quartz coating	1-pack	•	High polymers	Water based	Quartz structure	1 - 2.5 Kg/m²	62%	1 mm	10 gr/l	>5°C RH:<80%	4 hrs	7 hrs	24 hrs	48 hrs	Brush, Roller, Spray	White	-	-	43
NOXYDE®	Elastomeric rust preventive coating	1-pack	•	High polymers	Water based	Satin gloss	Brush/roller 200-300 gr./m², Airless 300-500 gr./m²	55-58%	350 µm	15 gr/l	8-55°C RH:<80%	1.5 hrs	3 hrs	24 hrs	2 weeks	Brush, Roller, Spray	See colour card	-	Water	21/25/ 26/28/52
PARACEM®	Acrylic wall paint	1-pack	•	Acrylic	Water based	Satin matt	7-10 m²/l.	46%	45 µm	55 gr/l	>5°C RH:<80%	40 min	2 hrs	4 hrs	1 day	Brush, Roller, Spray	See colour card/ColourShop	-	Water	44
PEGACRETE®	Concrete repair mortar	1-pack (mix with water)	•	Cement/Acrylic	Water based	Concrete-like finish	32 kg/m²	-	2 cm	0 gr/l	>5°C	-	-	2 days	1 month	Filling blad, Trowel	Concrete grey	-	Water	38
METAL CLADDING PRIMER	Water based primer for metal cladding	1-pack	•	Acrylic	Water based	Matt	12.5 m²/l.	43.7-44.5%	35 µm	14 gr/l	10-35°C RH:<85%	30 min	1 hr	1 hr	3 days	Brush, Roller, Spray	Light grey	80°C	Water	25
METAL CLADDING TOPCOAT	Water based topcoat for metal cladding	1-pack	•	Acrylic	Water based	Satin gloss	9-12 m²/l.	31-37%	35 µm	127 gr/l	>10°C RH:<80%	1 hr	5 hrs	24 hrs	2 days	Brush, Roller, Spray	See colour card	-	Water	25
PEGAGRAFF® HYDRO CLEANER	Anti-graffiti cleaning gel	1-pack	•	-	Solvent based	Gel	Depending on contamination/pollution	10%	-	647 gr/l	5-35°C	-	-	-	-	Stiff brush	Clear	-	-	46
PEGAGRAFF® HYDRO	Anti-graffiti coating	2-pack	•	Polyurethane/Acrylic	Water based	Satin	5 - 8 m²/l	40%	50 µm	20 gr/l	>5°C RH:<80%	2 hrs	4 hrs	5 hrs	48 hrs	Brush, Roller, Spray	Transparent	-	-	46
PEGAKOTE®	Water based epoxy floor coating	2-pack	•	Epoxy	Solvent free	Semi-gloss	1st coat 200-300 gr./m², 2nd coat 300-400 gr./m²	48-50%	100 µm	10 gr/l	>8°C RH:<80%	9 hrs	-	24 hrs	7 days	Brush, Roller, Spray	See colour card/ColourShop	-	Water	33
PEGALINK®	Universal adhesion primer	1-pack	•	Acrylic	Water based	Satin	10 m²/l.	36%	36 µm	45 gr/l	>5°C RH:<80%	20 min	1 hr	24 hrs	48 hrs	Brush, Roller, Spray	White/ColourShop	-	-	-
PEGANOX®	Elastomeric rust preventive coating	1-pack	•	Acrylic	Water based	Satin gloss	2 coats min. 200 gr./m²	48%	80 µm	15 gr/l	8-55°C RH:<80%	1 hr	2 hrs	6 hrs	48 hrs	Brush, Roller, Spray	See colour card	-	Airless spray: Water	22/25/28
PEGARUST®	Elastomeric rust preventive coating	1-pack	•	High polymers	Solvent based	Glossy	2-3 m²/l.	43-45%	170-195 µm	547 gr/l	> -5°C	-	-	24-48 hrs	1 week	Brush, Roller, Spray	Grey green, beige grey, red	-	Brush/Roller: Thinner 22	22
PEGASOL® QUARTZ	Two component floor coating	2-pack	•	Vinyl acrylic	Water based	Quartz structure	800 gr./m²	63%	315 µm	30 gr/l	>8°C RH:<80%	45 min	2 hrs	6 hrs	1 week	Brush, Roller	Grey	-	-	33
PEGASOL®	Two component floor coating	2-pack	•	Vinyl acrylic	Water based	Satin matt	150-200 gr./m²	50%	70 µm	30 gr/l	>8°C RH:<80%	25 min	5 hrs	6 hrs	1 week	Brush, Roller, Spray	See colour card	-	-	33
PORISOL®	Waterborne impregnation agent	1-pack	•	Vinyl high polymers	Water based	Glossy	3-10 m²/l.	48-50%	48 µm	0 gr/l	>5°C RH:<80%	30 min	-	1 hr	-	Brush, Roller	Clear	-	Water	-
PRIMER 44 HS	Binding primer	1-pack	•	Chlorinated rubber	Solvent based	Glossy	5-10 m²/l.	30-34%	32 µm	599 gr/l	5-35°C	1 hr	1 hr	12 hrs	24 hrs	Brush, Roller, Spray	Grey	-	-	56
PRIMER SB	Stabilising sealer and primer	1-pack	•	Polyurethane	Solvent based	Semi gloss	16 m²/l.	44%	25-35 µm	526 gr/l	>5°C	2 hrs	-	4-48 hrs	4 hrs	Brush, Roller, Spray	Clear	-	Thinner 160	49
RAPID SUPER	High viscosity paint stripper	1-pack	•	-	Solvent based	thixotropic liquid	0.5-2 m²/l.	-	-	1100 gr/l	-	-	-	-	-	Brush	-	-	-	-

This information is provided upon an indicative basis. For complete and up-to-date product details we refer to our online product data and safety datasheets: [www.rust-oleum.eu](http://www.rust-oleum.eu)

Technical information is subject to change without prior notice. \* Subject to local legislation \* Discoloration may occur with some paints above 65°C

GENERAL

General Purpose  
METAL

Noxydizing™  
METAL

Cladding Solutions  
METAL

FLOORS

EXTERIOR WALLS

ROOFS

HYGIENE

TECHNICAL